

## Thomson HS-4000M

High performance graphite filament compression packing for high speed rotating equipment and high temperature applications



### FEATURES / BENEFITS

- High speed capability
- Low friction - runs cooler, lasts longer - reduces flush water (greatly reduce product dilution).
- Broad chemical compatibility 0–14 pH.
- Non-asbestos - reduces handling costs.
- Non-abrasive - sleeves last longer.
- Reduces maintenance and parts costs.
- Maximizes equipment reliability and performance.
- Dissipates heat better than conventional compression packing materials. Increase MTBR - mean time between repair - less sleeve damage.
- Dimensionally stable fiber (less volume loss).

### TYPICAL APPLICATIONS

- High profile demanding applications; high speed rotating equipment to 5000+ fpm - for refiners, makeup liquor pumps, boiler feed pumps, condensate, end rings for flexible graphite die formed packing sets.
- Molybdenum disulphide surface coating is extremely chemical and thermally stable.

Typically recommend installation where the sleeve is in new condition.

### SPECIFICATIONS

#### Construction:

High purity, high strength graphite filament yarn treated with fine graphite powder to seal individual fibers. Surface coated with molybdenum disulphide. Square interbraid.

#### Temperatures:

Min: -328°F (-200°C)

Max:

To +850°F (+455°C) atmosphere

To +1200°F (+650°C) steam

#### Pressure, max:

To 500 psi (34.5 bar) rotary

Please contact A.R. Thomson Group for recommendations for valve or reciprocating applications.

#### Speed:

To 5000 fpm (25.4 m/s)

#### pH range:

0–14 (except strong oxidizers)

See reverse for ordering information.

## ORDERING INFORMATION - HS-4000M

Specify Thomson style, size and quantity (lbs) required.

Size	1/4"	5/16"	3/8"	7/16"	1/2"	5/8"	3/4"	20mm	7/8"	1"
<b>Approx. (ft/lb)</b>	33	21	16	10.5	8.5	6	4	3.9	3.4	2.2
<b>Std pkg (lbs)</b>	1/5	2/5	1/5	1/5	2/5	5	5/10	10	10	10

Also available in metric sizes, die formed pre-packaged sets, and specialty cut lengths.  
Contact A.R. Thomson Group for any special requirements.

## SHAFT SPEED CONVERSION CALCULATIONS

Feet per minute (fpm)	Meter per second (m/s)
Shaft / sleeve diameter (in) x RPM x 0.262 = fpm	Shaft / sleeve diameter (in) x RPM x 0.0013299 = m/s
Shaft / sleeve diameter (mm) x RPM x 0.0103 = fpm	Shaft / sleeve diameter (mm) x RPM x 0.0000524 = m/s

## AUTHORIZED DISTRIBUTOR

**Limitation of liability:** actual performance may vary and is determined by factors unique to a given application. It is recommended that care be taken in the selection and application of materials for hazardous services and controlled testing be undertaken to determine suitability for a specific application. A.R. Thomson Group does not make or imply any warranty of suitability for a particular purpose and is not liable for any damages arising from the use of the information in this sheet.



Locations across Canada to serve you. For your nearest branch, please visit [www.arthomson.com](http://www.arthomson.com)  
Copyright © A.R. Thomson Group - All rights reserved.