

Thomson ULTRA PAK

Flexible graphite c/w high purity carbon for anti-extrusion and abrasion-resistant corners.



FEATURES / BENEFITS

- High-purity carbon corners resist extrusion in worn equipment and high pressure applications.
- Spool stock convenience reduces inventory costs.
- No end rings in valves required. Reduces gland water consumption to 70–90%.

All-graphite/carbon construction:

- Maximizes reliability and stability in high temperatures. Also provides excellent chemical resistance.
- Dissipates heat quickly, so equipment runs cooler - requires less flush water.
- Less sleeve wear extends meantime between repair (MTBR).

TYPICAL APPLICATIONS

- High speed rotary applications (e.g. chemicals, paper stock, oil, solvents, steam, water, white water, boilerfeed water, soot blowers, valves, and agitators).
- Abrasive slurry applications.
- For installations with Thomson FLOW PRO™ bushings.

SPECIFICATIONS

Construction:

Flexible graphite yarn reinforced with high-purity, anti-extrusion carbon corners with graphite surface coating. Interlock braid.

Temperature, max:

To 850°F (455°C) air
To 1200°F (649°C) steam

Pressure, max:

To 500 psi (34 bar) pumps
To 5000 psi (344 bar) valves

Speed:

4800 fpm (22 m/s)
For higher shaft speeds, consult A.R. Thomson Group.

pH range:

0–14 (except strong oxidizers)

See reverse for ordering information.

ORDERING INFORMATION - ULTRA PAK

Specify Thomson style, size and quantity (lbs) required.

Size	1/4"	5/16"	3/8"	1/2"	5/8"	3/4"	7/8"	1"
Approx. (ft/lb)	25	16.6	12.4	7.2	4.7	3.5	2.6	2
Std pkg (lbs)	1/5/10	1/5/10	5/10	5/10/25	5/10/25	10/25	10/25	10/25

Also available in metric sizes, die formed pre-packaged sets, and specialty cut lengths.
Contact A.R. Thomson Group for any special requirements.

SHAFT SPEED CONVERSION CALCULATIONS

Feet per minute (fpm)	Meter per second (m/s)
Shaft / sleeve diameter (in) x RPM x 0.262 = fpm	Shaft / sleeve diameter (in) x RPM x 0.0013299 = m/s
Shaft / sleeve diameter (mm) x RPM x 0.0103 = fpm	Shaft / sleeve diameter (mm) x RPM x 0.0000524 = m/s

AUTHORIZED DISTRIBUTOR

Limitation of liability: actual performance may vary and is determined by factors unique to a given application. It is recommended that care be taken in the selection and application of materials for hazardous services and controlled testing be undertaken to determine suitability for a specific application. A.R. Thomson Group does not make or imply any warranty of suitability for a particular purpose and is not liable for any damages arising from the use of the information in this sheet.



Locations across Canada to serve you. For your nearest branch, please visit www.arthomson.com
Copyright © A.R. Thomson Group - All rights reserved. v3.0