

Thomson MOTION PAC X

Carbon fiber c/w Aflas[®] resilient elastomer core. Excellent choice for side, bottom and top entry agitators/mixers.



FEATURES / BENEFITS

- **Oversize square braid design** ensures tighter seal in worn or oversized stuffing boxes.
- **Carbon/Aflas** maximizes reliability and stability in equipment.
- Provides excellent chemical resistance.
- **Carbon filament reinforcement** resists extrusion in high pressure applications.
- Spool stock convenience.
- Maintains an effective seal in a high radial run out or bent shaft conditions (e.g. side entry agitators/mixers).

TYPICAL APPLICATIONS

- Most rotary applications
- Agitators/mixers
- Re-pulpers
- Thomson Sealing System FLOW PRO™ bushing, compression packing sealings rings.

SPECIFICATIONS

Construction:

High purity carbon yarn c/w Aflas elastomeric resilient core. Braid over core.

Temperature:

-30°F (-34°C) to +400°F (+204°C)

Pressure, max:

500 psi (35 bar) rotary centrifugal pumps
2500 psi (172 bar) valves

Speed:

To 3600 fpm (18.2 m/s)

pH range:

0–14 (except strong oxidizers)

See reverse for ordering information.

ORDERING INFORMATION - MOTION PAC X

Specify Thomson style, size and quantity (lbs) required.

Size	3/8"	1/2"	5/8"	3/4"	7/8"	1"
Approx. (ft/lb)	12	8.7	5.7	4	2.5	2
Std pkg (lbs)	5	5/25	5/25	5/25	10/25	10/25

Also available in metric sizes, die formed pre-packaged sets, and specialty cut lengths.
Contact A.R. Thomson Group for any special requirements.

SHAFT SPEED CONVERSION CALCULATIONS

Feet per minute (fpm)	Meter per second (m/s)
Shaft / sleeve diameter (in) x RPM x 0.262 = fpm	Shaft / sleeve diameter (in) x RPM x 0.0013299 = m/s
Shaft / sleeve diameter (mm) x RPM x 0.0103 = fpm	Shaft / sleeve diameter (mm) x RPM x 0.0000524 = m/s

AUTHORIZED DISTRIBUTOR

Limitation of liability: actual performance may vary and is determined by factors unique to a given application. It is recommended that care be taken in the selection and application of materials for hazardous services and controlled testing be undertaken to determine suitability for a specific application. A.R. Thomson Group does not make or imply any warranty of suitability for a particular purpose and is not liable for any damages arising from the use of the information in this sheet.



Locations across Canada to serve you. For your nearest branch, please visit www.arthomson.com
Copyright © A.R. Thomson Group - All rights reserved. v1.1