

CHEMLON® & ECLIPSE® Compatibility Chart

This compatibility chart is intended as a guide for selecting the appropriate type of product for the chemicals listed. However, this data should not be construed as advice to use or not to use without further testing or investigation, since variations in service conditions can influence suitability.

- 1 Suitable.
- 1* Suitable. Contact ARTG for Specific Parameters.
- 2 Depends on Operating Conditions.
- 3 Not Suitable.
- Insufficient Data. Contact ARTG.

	7500	7504	7510	7576
Abietic Acid	1	1	1	1
Acetaldehyde	1	1	1	1
Acetamide	1	1	1	1
Acetic Acid (Crude, Glacial, Pure)	1*	1*	1*	1*
Acetic Anhydride	1*	1*	1*	1*
Acetone	1	1	1	1
Acetonitrile	1	1	1	1
Acetophenone	1	1	1	1
2-Acetylaminofluorene	1	1	1	1
Acetylene	1	1	1	1
Acrolein	1*	1*	1*	1*
Acrylamide	1*	1*	1*	1*
Acrylic Acid	1*	1*	1*	1*
Acrylic Anhydride	1*	1*	1*	1*
Acrylonitrile	1*	1*	1*	1*
Air (150°F and below)	1	1	1	1
Allyl Acetate	1	1	1	1
Allyl Chloride	1	1	1	1
Allyl Methacrylate	1*	1*	1*	1*
Aluminum Chloride	1	1	1	1
Aluminum Fluoride	3	1*	1	1
Aluminum Hydroxide (Solid)	1	1	1	1
Aluminum Nitrate	1	1	1	1
Aluminum Sulfate	1	1	1	1
Alums	1	1	1	1
4-Aminodiphenyl	1	1	1	1
Ammonia (Gas 150°F & Below)	1	1	1	1
Ammonia (Gas Above 150°F)	1	1	1	1
Ammonia (Liquid, Anhydrous)	1	1	1	1
Ammonium Chloride	1	1	1	1
Ammonium Hydroxide	1	1	1	1
Ammonium Nitrate	1	1	1	1
Ammonium Phosphate, Monobasic	1	1	1	1
Ammonium Phosphate, Dibasic	1	1	1	1
Ammonium Phosphate, Tribasic	1	1	1	1
Ammonium Sulphate	1	1	1	1
Amyl Acetate	1	1	1	1
Amyl Alcohol	1	1	1	1
Aniline (Aniline Oil)	1	1	1	1
Aniline (Aniline Dyes)	1	1	1	1
o-Anisidine	1	1	1	1

	7500	7504	7510	7576
Aqua Regia	1	1	1	1
Aroclors	1	1	1	1
Asphalt	1	1	1	1
Aviation Gasoline	1	1	1	1
Barium Chloride	1	1	1	1
Barium Hydroxide	1	1	1	1
Barium Sulfide	1	1	1	1
Baygon	1	1	1	1
Beer	1	1	1	1
Benzaldehyde	1	1	1	1
Benzene (Benzol)	1	1	1	1
Benzidine	1	1	1	1
Benzoic Acid	1	1	1	1
Benzonitrile	1	1	1	1
Benzotrithloride	1	1	1	1
Benzoyl Chloride	1	1	1	1
Benzyl Alcohol	1	1	1	1
Benzyl Chloride	1	1	1	1
Bio-Diesel (B100)	1	1	1	1
Biphenyl	1	1	1	1
Bis (2-chloroethyl) ether	1	1	1	1
Bis (chloromethyl) ether	1	1	1	1
Bis (2-ethylhexyl) phthalate	1	1	1	1
Black Sulfate Liquor	3	1*	1	1
Blast Furnace Gas	1	1	1	1
Bleach (Sodium Hypochlorite)	1	1	1	1
Boiler Feed Water	1	1	1	1
Borax	1	1	1	1
Boric Acid	1	1	1	1
Brine (Calcium Chloride)	1	1	1	1
Bromine	1	1	1	1
Bromine Trifluoride	3	3	3	3
Bromoform	1	1	1	1
Bromomethane	1	1	1	1
Butadiene	1*	1*	1*	1*
Butane	1	1	1	1
2-Butanone	1	1	1	1
Butyl Acetate	1	1	1	1
Butyl Alcohol (Butanol)	1	1	1	1
n-Butyl Amine	1	1	1	1
tert-Butyl Amine	1	1	1	1

	7500	7504	7510	7576
Butyl Methacrylate	1*	1*	1*	1*
Butyric Acid	1	1	1	1
Calcium Bisulfite	1	1	1	1
Calcium Chloride	1	1	1	1
Calcium Cyanamide	1	1	1	1
Calcium Hydroxide	1*	1	1	1
Calcium Hypochlorite	1	1	1	1
Calcium Nitrate	1	1	1	1
Calflo AF	1	1	1	1
Calflo FG	1	1	1	1
Calflo HTF	1	1	1	1
Calflo LT	1	1	1	1
Cane Sugar Liquors	1	1	1	1
Caprolactam	1	1	1	1
Captan	1	1	1	1
Carbaryl	1	1	1	1
Carbolic Acid (Phenol)	1	1	1	1
Carbon Dioxide	1	1	1	1
Carbon Disulfide	1	1	1	1
Carbon Monoxide	1	1	1	1
Carbon Tetrachloride	1	1	1	1
Carbonic Acid	1	1	1	1
Cabonyl Sulfide	1	1	1	1
Castor Oil	1	1	1	1
Catechol	1	1	1	1
Caustic Soda	3	1*	1*	1*
Cetane (Hexadecane)	1	1	1	1
China Wood Oil	1	1	1	1
Chloramben	1	1	1	1
Chlorazotic Acid (Aqua Regia)	1	1	1	1
Chlordane	1	1	1	1
Chlorinated Solvents (Dry or Wet)	1	1	1	1
Chlorine (Dry)	1	1	1	1
Chlorine (Wet)	1	1	1	1
Chlorine Dioxide	1	1	1	1
Chlorine Trifluoride	3	3	3	3
Chloroacetic Acid	1	1	1	1
2-Chloroacetophenone	1	1	1	1
Chloroazotic Acid (Aqua Regia)	1	1	1	1
Chlorobenzene	1	1	1	1
Chlorobenzilate	1	1	1	1

CHEMLON® & ECLIPSE® Compatibility Chart

- 1 Suitable.
- 1* Suitable. Contact ARTG for Specific Parameters.
- 2 Depends on Operating Conditions.
- 3 Not Suitable.
- Insufficient Data. Contact ARTG.

	7500	7504	7510	7576
Chloroethane	1	1	1	1
Chloroethylene	1	1	1	1
Chloroform	1	1	1	1
Chloromethyl Methyl Ether	1	1	1	1
Chloronitrous Acid (Aqua Regia)	1	1	1	1
Chloroprene	1	1	1	1
Chlorosulfonic acid	1	1	1	1
Chrome Plating Solutions	1*	1*	1	1
Chromic Acid	1	1	1	1
Chromic Anhydride	1	1	1	1
Chromium Trioxide	1	1	1	1
Citric Acid	1	1	1	1
Coke Oven Gas	1	1	1	1
Copper Chloride	1	1	1	1
Copper Sulfate	1	1	1	1
Corn Oil	1	1	1	1
Cotton Seed Oil	1	1	1	1
Creosote	1	1	1	1
Cresols (Cresylic Acid)	1	1	1	1
Crotonic Acid	1	1	1	1
Crude Oil	1	1	1	1
Cumene	1	1	1	1
Cyclohexane	1	1	1	1
Cyclohexanone	1	1	1	1
2,4-D, Salts and Esters	1	1	1	1
Detergent Solutions	1*	1*	1	1
Diazomethane	1	1	1	1
Dibenzofuran	1	1	1	1
Dibenzylether	1	1	1	1
1,2-Dibromo-3-Chloropropane	1	1	1	1
Dibromoethane	1	1	1	1
Dibutyl Phthalate	1	1	1	1
Dibutyl Sebacate	1	1	1	1
o-Dichlorobenzene	1	1	1	1
1,4-Dichlorobenzene	1	1	1	1
3,3-Dichlorobenzidene	1	1	1	1
Dichloroethane (1,1 or 1,2)	1	1	1	1
1,1-Dichloroethylene	1*	1*	1*	1*
Dichloroethyl ether	1	1	1	1
Dichloromethane	1	1	1	1
1,2-Dichloropropane	1	1	1	1

	7500	7504	7510	7576
1,3-Dichloropropene	1	1	1	1
Dichlorvos	1	1	1	1
Diesel Oil	1	1	1	1
Diethanolamine	1	1	1	1
N, N-Diethylaniline	1	1	1	1
Diethyl Carbonate	1	1	1	1
Diethyl Sulfate	1	1	1	1
3,3-Dimethoxybenzidene	1	1	1	1
Dimethylaminoazobenzene	1	1	1	1
N, N-Dimethyl Aniline	1	1	1	1
3,3-Dimethylbenzidine	1	1	1	1
Dimethyl Carbamoyl Chloride	1	1	1	1
Dimethyl Ether	1	1	1	1
Dimethylformamide	1	1	1	1
Dimethyl Hydrazine (Unsymmetrical)	1	1	1	1
Dimethyl Phthalate	1	1	1	1
Dimethyl Sulfate	1	1	1	1
4,6-Dinitro-o-Cresol and Salts	1	1	1	1
2,4-Dinitrophenol	1	1	1	1
2,4-Dinitrotoluene	1	1	1	1
Dioxane	1	1	1	1
1,2-Diphenylhydrazine	1	1	1	1
Diphyl DT	1	1	1	1
Dowfrost	1	1	1	1
Dowfrost HD	1	1	1	1
Dowtherm 4000	1	1	1	1
Dowtherm A	1	1	1	1
Dowtherm E	1	1	1	1
Dowtherm G	1	1	1	1
Dowtherm HT	1	1	1	1
Dowtherm J	1	1	1	1
Dowtherm Q	1	1	1	1
Dowtherm SR-1	1	1	1	1
Epichlorohydrin	1	1	1	1
E85 (85% Ethanol, 15% Gas)	1	1	1	1
1,2-Epoxybutane	1	1	1	1
Ethane	1	1	1	1
Ethers	1	1	1	1
Ethyl Acetate	1	1	1	1
Ethyl Acrylate	1*	1*	1*	1*
Ethyl Alcohol (Ethanol)	1	1	1	1

	7500	7504	7510	7576
Ethylbenzene	1	1	1	1
Ethyl Carbamate	1	1	1	1
Ethyl Cellulose	1	1	1	1
Ethyl Chloride	1	1	1	1
Ethyl Ether	1	1	1	1
Ethyl Hexoate	1	1	1	1
Ethylene	1	1	1	1
Ethylene Bromide	1	1	1	1
Ethylene Dibromide	1	1	1	1
Ethylene Dichloride	1	1	1	1
Ethylene Glycol	1	1	1	1
Ethyleneimine	1*	1*	1	1
Ethylene Oxide	1*	1*	1*	1*
Ethylene Thiourea	1	1	1	1
Ethylidene Chloride	1	1	1	1
Ferric Chloride	1	1	1	1
Ferric Phosphate	1	1	1	1
Ferric Sulfate	1	1	1	1
Fluorine (Gas)	3	3	3	3
Fluorine (Liquid)	3	3	3	3
Flourine Dioxide	3	3	3	3
Formaldehyde	1*	1*	1*	1*
Formic Acid	1	1	1	1
Fuel Oil	1	1	1	1
Fuel Oil (Acid)	1	1	1	1
Furfural	1	1	1	1
Gasoline (Refined)	1	1	1	1
Gasoline (Sour)	1	1	1	1
Gelatin	1	1	1	1
Glucose	1	1	1	1
Glue, Protein-Based	1	1	1	1
Glycerine (Glycerol)	1	1	1	1
Glycol	1	1	1	1
Grain Alcohol	1	1	1	1
Grease (Petroleum-Based)	1	1	1	1
Green Sulfate Liquor	3	1*	1	1
Heptachlor	1	1	1	1
Heptane	1	1	1	1
Hexachlorobenzene	1	1	1	1
Hexachlorobutadiene	1	1	1	1
Hexachlorocyclopentadiene	1	1	1	1

Limitation of liability: actual performance may vary and is determined by factors unique to a given application. It is recommended that care be taken in the selection and application of materials for hazardous services and controlled testing be undertaken to determine suitability for a specific application. A.R. Thomson Group does not make or imply any warranty of suitability for a particular purpose and is not liable for any damages arising from the use of the information in this sheet. v3.0

CHEMLON® & ECLIPSE® Compatibility Chart

- 1 Suitable.
- 1* Suitable. Contact ARTG for Specific Parameters.
- 2 Depends on Operating Conditions.
- 3 Not Suitable.
- Insufficient Data. Contact ARTG.

	7500	7504	7510	7576
Hexachloroethane	1	1	1	1
Hexadecane	1	1	1	1
Hexamethylene Diisocyanate	1	1	1	1
Hexamethylphosphoramide	1	1	1	1
Hexane	1	1	1	1
Hexone	1	1	1	1
Hydraulic Oil (Mineral)	1	1	1	1
Hydraulic Oil (Synthetic, Phosphate Esters)	1	1	1	1
Hydrazine	1	1	1	1
Hydrobromic Acid	1	1	1	1
Hydrochloric Acid	1	1	1	1
Hydrocyanic Acid	1	1	1	1
Hydrofluoric Acid (Anhydrous)	3	3	3	1
Hydrofluoric Acid (Less Than 65%, Above 150°F)	3	3	1	1
Hydrofluoric Acid (65% To Anhydrous, Above 150°F)	3	3	-	1
Hydrofluoric Acid (Up To Anhydrous, Below 150°F)	3	3	1	1
Hydrofluorosilicic Acid	3	3	1	1
Hydrofluosilicic Acid	3	3	1	1
Hydrogen	1	1	1	1
Hydrogen Bromide	1	1	1	1
Hydrogen Fluoride	3	3	3	1
Hydrogen Peroxide	1	1	1	1
Hydrogen Sulfide, Wet or Dry (H ₂ S)	1	1	1	1
Hydroquinone	1	1	1	1
Iodomethane	1	1	1	1
Isobutane	1	1	1	1
Isooctane	1	1	1	1
Isophorone	1	1	1	1
Isopropyl Alcohol	1	1	1	1
Jet Fuels (JP Types)	1	1	1	1
Kerosene	1	1	1	1
Lacquer Solvents	1	1	1	1
Lacquers	1	1	1	1
Lactic Acid	1	1	1	1
Lime Saltpeter (Calcium Nitrates)	1	1	1	1
Lindane	1	1	1	1
Linseed Oil	1	1	1	1
Liquefied Petroleum Gas	1	1	1	1
Lithium Bromide	1	1	1	1
Lithium (Elemental)	3	3	3	3
Lubricating Oils (Refined)	1	1	1	1

	7500	7504	7510	7576
Lubricating Oils (Mineral or Petroleum Type)	1	1	1	1
Lubricating Oils (Sour)	1	1	1	1
Lye	3	1*	1*	1*
Magnesium Chloride	1	1	1	1
Magnesium Hydroxide	1	1	1	1
Magnesium Sulfate	1	1	1	1
Maleic Acid	1	1	1	1
Maleic Anhydride	1	1	1	1
Mercuric Chloride	1	1	1	1
Mercury	1	1	1	1
Methane	1	1	1	1
Methanol (Methyl Alcohol)	1	1	1	1
Methoxychlor	1	1	1	1
Methylacrylic Acid	1	1	1	1
2-Methylaziridine	-	-	1	1
Methyl Bromide	1	1	1	1
Methyl Chloride	1	1	1	1
Methyl Chloroform	1	1	1	1
4,4 Methylene Bis (2-Chloroaniline)	1	1	1	1
Methylene Chloride	1	1	1	1
4,4-Methylene Dianiline	1	1	1	1
Methylene Diphenyldiisocyanate	1	1	1	1
Methyl Ethyl Ketone (MEK)	1	1	1	1
Methyl Hydrazine	1	1	1	1
Methyl Iodide	1	1	1	1
Methyl Isobutyl Ketone (MIBK)	1	1	1	1
Methyl Isocyanate	1	1	1	1
Methyl Methacrylate	1*	1*	1*	1*
N-Methyl-2-Pyrrolidone (NMP)	1	1	1	1
Methyl Tert. Butyl Ether (MTBE)	1	1	1	1
Milk	1	1	1	1
Mineral Oils	1	1	1	1
Mobiltherm 600	1	1	1	1
Mobiltherm 603	1	1	1	1
Mobiltherm 605	1	1	1	1
Mobiltherm Light	1	1	1	1
Molten Alkali Metals	3	3	3	3
Monomethylamine	1	1	1	1
MultiTherm 100	1	1	1	1
MultiTherm 503	1	1	1	1
MultiTherm IG-2	1	1	1	1

	7500	7504	7510	7576
MultiTherm PG-1	1	1	1	1
Muriatic Acid	1	1	1	1
Naphtha	1	1	1	1
Naphthalene	1	1	1	1
Naphthols	1	1	1	1
Natural Gas	1	1	1	1
Nickel Chloride	1	1	1	1
Nickel Sulfate	1	1	1	1
Nitric Acid (Less Than 30%)	1	1	1	1
Nitric Acid (Above 30%)	1	1	1	1
Nitric Acid (Crude)	1	1	1	1
Nitric Acid (Red Fuming)	1	1	1	1
Nitrobenzene	1	1	1	1
4-Nitrobiphenyl	1	1	1	1
2-Nitro-butanol	1	1	1	1
Nitrocalcite (Calcium Nitrate)	1	1	1	1
Nitrogen	1	1	1	1
Nitrogen Tetroxide	1	1	1	1
Nitrohydrochloric Acid (Aqua Regia)	1	1	1	1
Nitromethane	1	1	1	1
2-Nitro-2-Methyl Propanol	1	1	1	1
Nitromuriatic Acid (Aqua Regia)	1	1	1	1
4-Nitrophenol	1	1	1	1
2-Nitropropane	1	1	1	1
N-Nitrosodimethylamine	1	1	1	1
N-Nitroso-N-Methylurea	1	1	1	1
N-Nitrosomorpholine	1	1	1	1
Norge Niter (Calcium Nitrate)	1	1	1	1
Norwegian Saltpeter (Calcium Nitrate)	1	1	1	1
N-Octadecyl Alcohol	1	1	1	1
Octane	1	1	1	1
Oil (Petroleum)	1	1	1	1
Oils (Animal & Vegetable)	1	1	1	1
Oleic Acid	1	1	1	1
Oleum	1	-	3	1
Orthodichlorobenzene	1	1*	1	1
Oxalic Acid	1	1	1	1
Oxygen (Gas)	1*	1*	1*	1*
Ozone	1*	1*	1*	1*
Palmitic Acid	1	1	1	1
Paraffin	1	1	1	1

Limitation of liability: actual performance may vary and is determined by factors unique to a given application. It is recommended that care be taken in the selection and application of materials for hazardous services and controlled testing be undertaken to determine suitability for a specific application. A.R. Thomson Group does not make or imply any warranty of suitability for a particular purpose and is not liable for any damages arising from the use of the information in this sheet. v3.0

CHEMLON® & ECLIPSE® Compatibility Chart

- 1 Suitable.
- 1* Suitable. Contact ARTG for Specific Parameters.
- 2 Depends on Operating Conditions.
- 3 Not Suitable.
- Insufficient Data. Contact ARTG.

	7500	7504	7510	7576
Paratherm HE	1	1	1	1
Paratherm NF	1	1	1	1
Parathion	1	1	1	1
Paraxylene	1	1	1	1
Pentachloronitrobenzene	1	1	1	1
Pentachlorophenol	1	1	1	1
Pentane	1	1	1	1
Perchloric Acid	1	1	1	1
Perchloroethylene	1	1	1	1
Petroleum Oils (Crude)	1	1	1	1
Petroleum Oils (Refined)	1	1	1	1
Phenol	1	1	1	1
p-Phenylenediamine	1	1	1	1
Phosgene	1	1	1	1
Phosphate Esters	1	1	1	1
Phosphine	1	1	1	1
Phosphoric Acid (Crude)	3	3	1	1
Phosphoric Acid (Pure, Less Than 45%)	1	1	1	1
Phosphoric Acid (Pure, Above 45%, 150°F & Below)	1*	1*	1	1
Phosphoric Acid (Pure, Above 45%, Above 150°F)	1*	1*	1	1
Phosphorus (Elemental)	1	1	1	1
Phosphorus Pentachloride	1	1	1	1
Phthalic Acid	1	1	1	1
Phthalic Anhydride	1	1	1	1
Picric Acid (Water Solution)	1	1	1	1
Pinene	1	1	1	1
Piperidine	1	1	1	1
Polyacrylonitrile	1	1	1	1
Polychlorinated Biphenyls	1	1	1	1
Potash (Potassium Carbonate)	1	1	1	1
Potassium Acetate	1	1	1	1
Potassium Bichromate	1	1	1	1
Potassium Chromate (Red)	1	1	1	1
Potassium Cyanide	1	1	1	1
Potassium Dichromate	1	1	1	1
Potassium (Elemental)	3	3	3	3
Potassium Hydroxide	3	1*	1*	1*
Potassium Nitrate	1	1	1	1
Potassium Permanganate	1	1	1	1
Potassium Sulfate	1	1	1	1
Producer Gas	1	1	1	1

	7500	7504	7510	7576
Propane	1	1	1	1
1,3-Propane Sultone	1	1	1	1
Beta-Propiolactone	1	1	1	1
Propionaldehyde	1	1	1	1
Propoxur (Baygon)	1	1	1	1
Propyl Alcohol	1	1	1	1
Propyl Nitrate	1	1	1	1
Propylene	1	1	1	1
Propylene Dichloride	1	1	1	1
Propylene Glycol	1	1	1	1
Propylene Oxide	1	1	1	1
1,2-Propylenimine	-	-	1	1
Prussic acid (Hydrocyanic Acid)	1	1	1	1
Pyridine	1	1	1	1
Quinoline	1	1	1	1
Quinone	1	1	1	1
Refrigerant 10	1	1	1	1
Refrigerant 11	1	1	1	1
Refrigerant 12	1	1	1	1
Refrigerant 13	1	1	1	1
Refrigerant 13B1	1	1	1	1
Refrigerant 21	1	1	1	1
Refrigerant 22	1	1	1	1
Refrigerant 23	1	1	1	1
Refrigerant 31	1	1	1	1
Refrigerant 32	1	1	1	1
Refrigerant 112	1	1	1	1
Refrigerant 113	1	1	1	1
Refrigerant 114	1	1	1	1
Refrigerant 114B2	1	1	1	1
Refrigerant 115	1	1	1	1
Refrigerant 123	1	1	1	1
Refrigerant 124	1	1	1	1
Refrigerant 125	1	1	1	1
Refrigerant 134A	1	1	1	1
Refrigerant 141B	1	1	1	1
Refrigerant 142B	1	1	1	1
Refrigerant 143A	1	1	1	1
Refrigerant 152A	1	1	1	1
Refrigerant 218	1	1	1	1
Refrigerant 290 (Propane)	1	1	1	1

	7500	7504	7510	7576
Refrigerant 500	1	1	1	1
Refrigerant 502	1	1	1	1
Refrigerant 503	1	1	1	1
Refrigerant 507	1	1	1	1
Refrigerant 717 (Ammonia)	1	1	1	1
Refrigerant 744 (Carbon Dioxide)	1	1	1	1
Refrigerant C316	1	1	1	1
Refrigerant C318	1	1	1	1
Refrigerant HP62	1	1	1	1
Refrigerant HP80	1	1	1	1
Refrigerant HP81	1	1	1	1
Salt Water/Brine	1	1	1	1
Saltpeter (Potassium Nitrate)	1	1	1	1
2, 4-D Salts & Esters	1	1	1	1
Sewage	1	1	1	1
Silver Nitrate	1	1	1	1
Skydrols	1	1	1	1
Soap Solutions	1	1	1	1
Soda Ash (Sodium Carbonate)	1	1	1	1
Sodium Bicarbonate (Baking Soda)	1	1	1	1
Sodium Bisulfate (Dry)	1	1	1	1
Sodium Bisulfite	1	1	1	1
Sodium Chlorate	1	1	1	1
Sodium Chloride	1	1	1	1
Sodium Cyanide	3	3	1	1
Sodium (Elemental)	3	3	3	3
Sodium Hydroxide	3	1*	1*	1*
Sodium Hypochlorite (Bleach)	1	1	1	1
Sodium Metaborate Peroxyhydrate	1	1	1	1
Sodium Metaphosphate	1*	1	1	1
Sodium Nitrate	1	1	1	1
Sodium Perborate	1	1	1	1
Sodium Peroxide	1	1	1	1
Sodium Phosphate (Monobasic)	1	1	1	1
Sodium Phosphate (Dibasic)	1*	1*	1	1
Sodium Phosphate (Tribasic)	3	1*	1	1
Sodium Silicate	1*	1*	1	1
Sodium Sulfate	1	1	1	1
Sodium Sulfide	1	1	1	1
Sodium Superoxide	1	1	1	1
Sodium Thiosulfate (Hypo)	1	1	1	1

Limitation of liability: actual performance may vary and is determined by factors unique to a given application. It is recommended that care be taken in the selection and application of materials for hazardous services and controlled testing be undertaken to determine suitability for a specific application. A.R. Thomson Group does not make or imply any warranty of suitability for a particular purpose and is not liable for any damages arising from the use of the information in this sheet. v3.0

CHEMLON® & ECLIPSE® Compatibility Chart

- 1 Suitable.
- 1* Suitable. Contact ARTG for Specific Parameters.
- 2 Depends on Operating Conditions.
- 3 Not Suitable.
- Insufficient Data. Contact ARTG.

	7500	7504	7510	7576
Soybean Oil	1	1	1	1
Stannic Chloride	1	1	1	1
Steam (Saturated, to 150 psig)	1	1	1	1
Stearic Acid	1	1	1	1
Stoddard Solvent	1	1	1	1
Styrene	1*	1*	1*	1*
Styrene Oxide	1	1	1	1
Sulfur Chloride	1	1	1	1
Sulfur Dioxide	1	1	1	1
Sulfur (Molten)	1	1	1	1
Sulfur Trioxide (Wet or Dry)	1	1	1	1
Sulfuric Acid (10%, 150°F & Below)	1	1	1	1
Sulfuric Acid (10%, Above 150°F)	1	1	1	1
Sulfuric Acid (10-75%, 500°F & Below)	1	1	1	1
Sulfuric Acid (75-98%, 150°F & Below)	1	1	1*	1
Sulfuric Acid (75-98%, 150°F to 500°F)	1	1*	1*	1
Sulfuric Acid (Fuming)	1	-	3	1
Sulfurous Acid	1	1	1	1
Syltherm 800	1	1	1	1
Syltherm XLT	1	1	1	1
Tannic Acid	1	1	1	1
Tar A	1	1	1	1
Tartaric Acid	1	1	1	1
2,3,7,8-TCDB-p-Dioxin	1	1	1	1
Tertiary Butyl Amine	1	1	1	1
Tetrabromoethane	1	1	1	1
Tetrachloroethane	1	1	1	1
Tetrachloroethylene	1	1	1	1
Tetrahydrofuran (THF)	1	1	1	1
Therminol 44	1	1	1	1
Therminol 55	1	1	1	1
Therminol 59	1	1	1	1
Therminol 60	1	1	1	1
Therminol 66	1	1	1	1
Therminol 75	1	1	1	1
Therminol D12	1	1	1	1
Therminol LT	1	1	1	1
Therminol VP-1	1	1	1	1
Therminol XP	1	1	1	1
Thionyl Chloride	1	1	1	1
Titanium Sulfate	1	1	1	1

	7500	7504	7510	7576
Titanium Tetrachloride	1	1	1	1
Toluene	1	1	1	1
2,4-Toluenediamine	1	1	1	1
2,4-Toluenediisocyanate	1	1	1	1
Toluene Sulfonic Acid	1	1	1	1
o-Toluidine	1	1	1	1
Toxaphene	1	1	1	1
Transformer Oil (Mineral Type)	1	1	1	1
Transmission Fluid A	1	1	1	1
Trichloroacetic Acid	1	1	1	1
1,2,4-Trichlorobenzene	1	1	1	1
1,1,2-Trichloroethane	1	1	1	1
Trichloroethylene	1	1	1	1
2,4,5-Trichlorophenol	1	1	1	1
2,4,6-Trichlorophenol	1	1	1	1
Tricresylphosphate	1	1	1	1
Triethanolamine	1	1	1	1
Triethyl Aluminum	1	1	1	1
Triethylamine	1	1	1	1
Trifluralin	1	1	1	1
2,2,4-Trimethylpentane	1	1	1	1
Tung Oil	1	1	1	1
Turpentine	1	1	1	1
UCON Heat Transfer Fluid 500	1	1	1	1
UCON Process Fluid WS	1	1	1	1
Urea (150°F & Below)	1	1	1	1
Urea (Above 150°F)	1	1	1	1
Varnish	1	1	1	1
Vegetable Oil	1	1	1	1
Vinegar	1	1	1	1
Vinyl Acetate	1*	1*	1*	1*
Vinyl Bromide	1*	1*	1*	1*
Vinyl Chloride	1*	1*	1*	1*
Vinylidene Chloride	1*	1*	1*	1*
Vinyl Methacrylate	1	1	1	1
Water (Acid Mine, With Oxidizing Salt)	1	1	1	1
Water (Acid Mine, No Oxidizing Salt)	1	1	1	1
Water (Distilled)	1	1	1	1
Return Condensate	1	1	1	1
Seawater	1	1	1	1
Tap Water	1	1	1	1

	7500	7504	7510	7576
Whiskey & Wines	1	1	1	1
Wood Alcohol	1	1	1	1
Xceltherm 550	1	1	1	1
Xceltherm 600	1	1	1	1
Xceltherm MK1	1	1	1	1
Xceltherm XT	1	1	1	1
Xylene	1	1	1	1
Zinc Chloride	1	1	1	1
Zinc Sulfate	1	1	1	1

Limitation of liability: actual performance may vary and is determined by factors unique to a given application. It is recommended that care be taken in the selection and application of materials for hazardous services and controlled testing be undertaken to determine suitability for a specific application. A.R. Thomson Group does not make or imply any warranty of suitability for a particular purpose and is not liable for any damages arising from the use of the information in this sheet. v3.0